

PBO-JOINT

PBO fibre connector for FRCM system

Along with its **MX-JOINT inorganic matrix**, the **PBO-JOINT** connection system interconnects existing masonry and concrete structures by means of FRCM **PBO** structural strengthening systems.

The fibre connector is prepared on site. It consists of a bundle of continuous parallel fibres or strands gathered within a tubular elastic net made of polyester, polyamide and latex fibres. The net can be extended both longitudinally and transversely and can be removed. The bundle of fibres becomes rigid when it is impregnated with the appropriate MX-JOINT inorganic matrix, and is inserted into a specially made hole in the masonry and/or reinforced concrete structural element.

FIELDS OF APPLICATION

- Adapting and upgrading the static and anti-seismic behaviour of masonry and reinforced concrete buildings.
- Structural strengthening to loadbearing walls (piers) and spandrels of masonry buildings, when the FRCM system is applied to one face only of the wall
- Structural strengthening to loadbearing walls (piers) and spandrels of masonry buildings, when the FRCM system is applied to multiple-leaf and/or rubble core masonry.
- Structural strengthening to masonry corners and horizontal bandaging at floor levels.
- Structural strengthening to eaves ring beams in masonry walls.
- Structural strengthening to masonry arches, vaults, and domes.
- Structural strengthening to infrastructure works built from masonry.
- Shear strengthening to reinforced concrete beams.
- Strengthening to resist combined axial and flexural forces in reinforced concrete columns.
- Structural strengthening to infrastructure works in reinforced concrete.
- Anti-overturn systems for internal partitions and external walls.

ADVANTAGES AND PROPERTIES OF THE SYSTEM

- Increases the capacity of the PBO-FRCM strengthening system to adhere to the existing support.
- Increases the capacity of the PBO-FRCM system to adhere to the existing masonry support when it is applied to one face only.
- Application of the face-to-face PBO fibre connector increases adhesion capacity to the masonry support in multi-leaf and/or rubble-core masonry.
- Increased adhesion capacity of the PBO FRCM system to the concrete support when shear strengthening is applied to reinforced concrete beams.
- Increased adhesion capacity of the PBO FRCM system to the concrete support when strengthening is applied to reinforced concrete walls.
- Continuous force transfer to the structure is created by the PBO-FRCM strengthening system when it is applied to strengthening against combined axial and flexural forces in reinforced concrete columns.
- Creation of constraints when the PBO fibre connector is inserted into masonry and reinforced concrete structures.
- The system can also be applied to damp supports without any need for special protection.
- The fibre bundle is easy to place and handle.

METHOD OF USE AND INSTALLATION

SUPPORT PREPARATION

- Prepare the support and install the FRCM system for masonry and concrete (see technical data sheet for the **PBO-MESH 22/22 + MX-PBO MASONRY**, **PBO-MESH 44 + MX-PBO MASONRY**, **PBO-MESH 105 + MX-PBO CONCRETE**, **PBO-MESH 70/18 + MX-PBO CONCRETE**, **PBO-MESH 88 + MX-PBO CONCRETE**, **PBO-MESH 10/10 + MX-PBO MASONRY**) systems.

- Drill holes in the masonry or concrete support of minimum diameter 14 mm for the **3 mm PBO-JOINT**, and 16 mm for the **6 mm PBO-JOINT**.
- The depth, inclination, and pitch of the connection systems must accord with the design requirements, and with prior approval by the Director of Works.
- It is recommended to use a drill whose technical characteristics are suitable for the consistency of the material to be drilled.
- Eliminate dust and incoherent parts (e.g. with compressed air) from inside the hole that were produced by drilling.
- The connection system must only be installed after the inorganic matrix of the previously installed FRCM reinforcement system has completely hardened.

PREPARATION OF THE MX-JOINT INORGANIC MATRIX

- Open the 5 kg bucket of **MX-JOINT** inorganic matrix.
- Pour in 90% of the required total water content (0.95 litres of clean water) and mix for approx. three minutes.
- Using a paddle mixer drill at low speed, mix without stopping until a homogeneous lump-free mixture is obtained.

GROUTING INTO THE HOLE

- Add the remainder of the water (0.10 litres of clean water) and continue until the mixture is homogeneous, free of lumps, and has a "pasty/creamy" consistency.
- Pour the contents into the Ruregold **GUN**.
- Using the Ruregold **GUN**, inject the **MX-JOINT** inorganic matrix into the hole.

IMPREGNATING THE FIBRE CONNECTOR

- Add the remainder of the water (0.35 litres of clean water) and continue mixing until a homogeneous and lump-free mixture of "fluid" consistency is obtained.
- Impregnate the part of the connector that was prepared previously.

APPLICATION OF THE CONNECTION SYSTEM

- Carefully wet the hole without allowing any excess water to stagnate.
- Cut the **PBO-JOINT** fibre connector to the required length. Take into consideration the portion that will be inserted into the hole (approx. 3/5 of the depth of the hole) increased as appropriate (about 15 - 30 cm), to account for the portion that will be spread out on the FRCM system. Cut the fibre connector to size. (or use the special **Ruregold SCISSORS**).

- From the end of the **PBO-JOINT** fibre connector, pull out the fibres from the tubular elastic net that contains it, taking care not to extract the fibres completely, but only the length that is to be inserted into the hole. → Important: use one hand to hold the end of the part of the connector that is retained within the tubular elastic net.
- Open the bundle of fibres that are now free of the tubular net, ready to be impregnated with the **MX-JOINT** matrix.
- Impregnate the part of the connector that has been pulled out, in the semi-fluid **MX-JOINT** matrix (the steps for preparing the **MX-JOINT** matrix are given below).
- Reposition the tubular elastic net on the portion of the connector that is now impregnated with the semi-fluid inorganic matrix.
- Wait for the now-impregnated part of the connector to harden (**the hardening phase must continue until the affected part of the fibre connector has become sufficiently manoeuvrable inside the hole, without waiting for the matrix gripping and hardening phase to complete**).
- Fill the hole with **MX-JOINT** inorganic matrix. If necessary use the special Ruregold **GUN**, which has a nozzle with a rigid extension and a flexible connection and is ideal even in the most difficult positions.
- Insert the portion of the **PBO-JOINT** connector, previously impregnated with **MX-JOINT** matrix, into the hole, being sure to insert it deeply (approx. 3/5 of the depth of the hole).
- Remove the elastic tubular net containing the portion of the **PBO-JOINT** connector that is protruding from the hole.
- When the FRCM strengthening system has been installed and has hardened, apply a first layer (approx. thickness 3- 5 mm) of **MX-JOINT** matrix around the hole into which the impregnated portion of the **PBO-JOINT** connector was inserted.
- Fan out the bundle of fibres of the part of the **PBO-JOINT** connector that is protruding from the hole and then, using a smooth metal spatula and applying light pressure, push it into the first layer of **MX-JOINT** matrix.
- Then apply a second layer of **MX-JOINT** inorganic matrix (approx. thickness 3- 5 mm) on to the fanned-out fibres to completely cover the previously fanned-out portion of the connector.
- The operations just described should be carried out wet on wet.

TECHNICAL CHARACTERISTICS

PROPERTIES OF PBO FIBRE (polyparaphenylene benzobisoxazole)	
Tenacity	5.80 GPa
Young's modulus of elasticity	270 GPa
Ultimate elongation	2.5 %
Density	1.56 g/cm ³
Decomposition temperature	+ 650 °C
Riferimento normativo delle fibre	ISO 16120 – 1/4

PROPERTIES OF THE PBO-JOINT FIBRE CONNECTOR		
Nominal diameter	3 mm	6 mm
Resistant cross-section of the connector	8.80 mm ²	17.61 mm ²
Tensile strength (average value)	2789 MPa	2983 MPa
Tensile strength (characteristic value)	2413 MPa	1860 MPa
Ultimate strain (characteristic value)	2.14 %	1.95 %
Young's modulus of elasticity (average value)	198 GPa	238 GPa
Packaging	10-metre dispenser	
Storage	In a dry place away from heat sources	
Certification	ETA 19/0361 dated 16/10/2019	

PROPERTIES OF MX-JOINT INORGANIC MATRIX	
Density	approx. 1800 kg/m ³
Application temperature	from +5°C to +35°C
Compressive strength at 28 days	≥ 40 MPa
Flexural strength at 28 days	≥ 3 MPa
Youngs modulus of elasticity at 28 days	≥ 18.50 GPa
Consumption	approx. 0.8 - 1.0 kg/m
Reaction to fire (EN 13501-1)	Euroclass A2
Packaging	Disposable wooden pallets with 72 buckets per 5 kg pallet = 360 kg of product
Storage conditions	In original packaging, under cover, in a cool, dry, unventilated place
Shelf life (European Directive 2003/53/EC)	Not more than twenty-four (24) months from packing date
Safety data sheet	Available from www.ruregold.com

GENERAL NOTES/GUIDANCE

As directed by the Designer, install the **FRCM strengthening system for connections** consisting of the **PBO-JOINT** connector and the **MX-JOINT** inorganic matrix. One length of the fibre bundle will be impregnated and inserted into the hole, and the other length will be fanned out on to the FRCM connection after installation. Ensure that the support is prepared as necessary.

Store the material in a covered and dry place away from substances that could compromise its integrity and correct application. Appropriate site PPE must be worn when installing the FRCM system. For further technical information, contact Ruregold Technical Support on +39 02.48011962 – info@ruregold.it.

SPECIFICATION ITEM

Supply and installation of a connection system to support the **FRCM structural strengthening** and consisting of Ruregold unidirectional **PBO-JOINT** PBO fibres of nominal diameter 3/6 mm. The PBO fibre has a density of 1.56 g/cm³, tensile strength/toughness approx. 5.8 GPa, maximum Young's modulus of elasticity 270 GPa, and ultimate strain of 2.5%. The system is coupled to an inorganic matrix of type Ruregold **MX-JOINT** specific for connections, of compression strength > 40 MPa and flexural strength > 3 MPa. The connection system in unidirectional PBO fibres enables coupling connections to be created between the existing structures and the structural strengthening and to obtain,

where required, the necessary continuity of the reinforcement. Creation of connection for anti-overtum protection. Face-to-face connections at corners and separated intersecting walls. Connection system consistent with CNR-DT 215/2018 (Guide for the Design and Construction of Externally Bonded Fibre Reinforced Inorganic Matrix Systems for Strengthening Existing Structures, issued by Italian national research council CNR - Advisory committee on technical recommendations for construction). Fire reaction classification of the system meets the requirements of EN 13501-1: A2 – s1, d0. Preparation of the surfaces and installation of the system must follow the manufacturer's instructions.

Edition 06/2021

This technical data sheet is not a specification.

Although the information provided is the outcome of our best experience and knowledge, it is indicative only. The user is responsible for determining whether the product is suitable or unsuitable for the intended use, and accepts all liability arising from the use of that product. Ruregold reserves the right to change the packaging and the quantity it contains, without notice. Verify that the revision of the data sheet is current. Ruregold products are intended for professional use only.



Ruregold s.r.l.
Via Achille Grandi, 5
20056 • Trezzo sull'Adda (MI) • Italy
Ruregold.com • +39 02.48011962